

JONESBORO RED™

POLISHED FINISH

THERMALED FINISH



J.C. STONE INC.
Quarriers / Fabricators of Landscape & Building Stone

JONESBORO RED™

STONE INFORMATION:

Quarry Location: Jonesboro, Maine

Available In: Blocks, Slabs, Cut to Size

Popular Applications: Architectural and Landscaping Stone, Building Cladding, Monuments, Countertops, Benches, Chimneys, Curbing, Steps, Paving Stones

Technical Information:

	English	Metric	Test Method
Absorption by weight	.27%	.27%	ASTM C97-47
Density (Specific gravity)	169 lbs/ft ³ (2.62)	2,707 kg/m ³ (2.62)	ASTM C97-47
Compression strength	41,000 psi	282.8 MPa	ASTM C170-50/90
Modulus of rupture	2,285 psi	15.8 MPa	ASTM C99-52
Abrasion resistance (hardness)	99 HA	n/a	ASTM C241-51
Flexural strength	n/a	n/a	ASTM C880-89

CONTACT INFORMATION:

Stone Center :

545 Rockland Rd (Rt.17)
Jefferson, Maine 04348

Mailing Address:

P.O. Box 177
Washington, ME 04574

Phone:


(207) 549-4729

Fax:

(207) 549-4032

Website:

www.jcstoneinc.com



J.C. STONE^{INC.}

Quarriers / Fabricators of Landscape & Building Stone

DISCLAIMER:

Stone is a natural product and will vary in color. Due to printing processes, the images published herein are intended for reference purposes only. In circumstances where color matching is critical, please contact us for a physical stone sample.

PHONE: 207.549.4729

FAX: 207.549.4032

WWW.JCSTONEINC.COM