

RIPTIDE WHITE™

STONE INFORMATION:

Quarry Location: Jay, Maine

Available In: Blocks, Slabs, Cut to Size

Popular Applications: Architectural and Landscaping Stone, Building Cladding, Monuments, Countertops, Benches, Chimneys, Curbing, Steps, Paving Stones

Technical Information:

	English	Metric	Test Method
Absorption by weight	.27%	.27%	ASTM C97-47
Density (Specific gravity)	168 lbs/ft ³ (2.62)	2,630kg/m ³	ASTM C97-47
Compression strength	27,700 psi	191Mpa	ASTM C170-50/90
Modulus of rupture	2,244 psi	15.5Mpa	ASTM C99-52
Abrasion resistance (hardness)	68 HA	68 HA	ASTM C241-51
Flexural strength	2,020 psi	13.9Mpa	ASTM C880-89

CONTACT INFORMATION:

Stone Center :

539 Rockland Rd (Rt.17)
Jefferson, Maine 04348

Phone:


(207) 549-4729

Fax:

(207) 549-4032

Website:

www.jcstoneinc.com



J.C. STONE^{INC.}
Quarriers / Fabricators of Landscape & Building Stone

DISCLAIMER:

Stone is a natural product and will vary in color. Due to printing processes, the images published herein are intended for reference purposes only. In circumstances where color matching is critical, please contact us for a physical stone sample.